

クレモナSロープ(Kuralon S Rope)

原料: ポリエステル混紡ビニロン 紡績糸
比重: 1.33

寸 法		最低引張強度				標準質量 (kg / 200m)			
直 径	周 径	NK 規格		当社規格		NK 規格	三つ打ち (普通打)	三つ打ち (硬打)	クロス
mm	inch	kN	tf	kN	tf				
3	3/8			1.18	0.12		1.13	1.16	
4	1/2			2.06	0.21		2.02	2.08	
5	5/8			3.04	0.31		3.15	3.24	
6	3/4			4.31	0.44		4.54	4.68	
7	7/8			5.79	0.59		6.17	6.36	
8	1			7.35	0.75		8.06	8.30	8.30
-9B,-9C -10B,-10C	9			9.22	0.94		10.2	10.5	10.5
	10			11.4	1.16		12.5	12.9	12.9
	11			13.7	1.40		15.1	15.6	15.6
	12			15.6	1.59		18.0	18.5	18.5
	14			20.7	2.11		24.5	25.2	25.2
	16			26.5	2.70		32.0	33.0	33.0
	18			33.0	3.36		40.5	41.7	41.7
	20			40.0	4.08		50.0	51.5	50.0
	22			49.2	5.02		60.5	62.3	60.5
	24			57.9	5.90		72.0	74.2	72.0
	26			67.1	6.84		84.5	87.0	84.5
	28			77.0	7.85		98.0	101	98.0
	30			87.5	8.92		112	115	112
	32			98.1	10.0		127	131	127
	34			110	11.2		144	148	144
	35			117	11.9		153	158	153
	36			123	12.5		161	166	161
	38			135	13.8		180	185	180
	40			149	15.2		199	205	199
	42			163	16.6		220	227	220
	45			185	18.9		252	260	252
	48			209	21.3		287	296	287
	50			225	22.9		311	320	311
	55			269	27.4		375	386	375
	60			315	32.1		446	459	446
	65			366	37.3		524	540	524
	70			419	42.7		608	626	608
	75			477	48.6		698	719	698
	80			536	54.7		794	818	794
	85			600	61.2		896	923	896
	90			667	68.0		1000	1030	1000
	95			737	75.2		1120	1150	1120
	100			811	82.7		1240	1280	1240
	110			967	98.6		1500	1550	1500
	120			1140	116		1790	1840	1790

(注) 1. 湿潤時の強度は乾時の約90%です。
2. 伸度は乾時25~30%、湿潤時30~35%です。