

Atlas Way, Sheffield, UK, S4 7QQ Tel: +44 (0)114 225 0600

Fax: +44 (0)114 225 0600

### **MATERIAL DATA SHEET**

Material/Trade Name - NdFeB

#### 1- Substance Identification

Material/Trade Name - NdFeB

Material Type - Neodymium Iron Boron
Company - Eclipse Magnetics Ltd
Address - Atlas Way, Atlas North,

Sheffield S4 7QQ

Telephone - 0114 2250600

E-Mail - info@eclipsemagnetics.com

#### 2-Substance

NdFeB

#### 3-REACH

Neodymium materials contain no SVHC (Substances of Very High Concern) either in ingredients or in preparation

#### 4- Hazard Identification

# THIS MATERIAL POSES A FIRE RISK WITH THE FINE DUST PRODUCED WHEN MACHINING.

Very fine powder, 200 mesh is rated as a weak explosive hazard when suspended in air.

Flash Point - 515°C

#### 5- First Aid Measures

Inhalation - Remove to fresh air area

Inform first aider

Eyes - Flush dust from eyes th water

Inform first aider

Skin - Wash with soap and water

Inform first aider

Ingestion - Give plenty of water to drink, do not induce vomiting

Inform first aider



Atlas Way, Sheffield, UK, S4 7QQ

Tel: +44 (0)114 225 0600 Fax: +44 (0)114 225 0600

#### 6- Fire Prevention

Use a smothering agent such as sand or graphite powder

## 7- Handling & Storage of Magnetised Products

Due care should be taken when handling fully magnetised material as physical injury may occur through entrapment of body parts caused by the inadvertent attraction of magnetised material to other similar or ferro-magnetic material.

Close proximity to the magnetic field from magnetised material may effect the operation of heart pacemakers and other electronic equipment including Computers & Mobile Phones. Credit Cards can also be affected.

## 8a - Properties (Magnetic)

	Br	bHc	iHc	BH Max	Magnetising
	(Gauss)	(Oersted)	(Oersted)	(MGO)	Force
					(Oersted)
N30	11,600	10,000	11,000	30	30,000
N30H	11,600	10,000	11,000	30	30,000
N30SH	11,600	10,000	11,000	30	30,000
N35	12,000	10,900	12,000	35	30,000
N35H	12,000	10,900	12,000	35	30,000
N35SH	12,000	10,900	12,000	35	30,000
N38	12,300	11,300	12,000	38	30,000
N38H	12,300	11,300	12,000	38	30,000
N38SH	12,300	11,300	12,000	38	30,000
N40	12,750	11,400	12,000	40	30,000
N40H	12,750	11,400	12,000	40	30,000
N40SH	12,750	11,400	12,000	40	30,000
N42	13,100	10,900	12,000	42	30,000
N45	13,500	11,300	12,000	45	30,000



Atlas Way, Sheffield, UK, S4 7QQ Tel: +44 (0)114 225 0600

Tel: +44 (0)114 225 0600 Fax: +44 (0)114 225 0600

# 8b - Properties (Thermal)

	Reversible Temperature Coefficient of Br (%change/°C)	Curie Temperature (°C)	Maximum Working Temp (°C)
N30	-0.09	310	80
N30H	-0.09	310	120
N30SH	-0.09	310	150
N35	-0.09	310	80
N35H	-0.09	310	120
N35SH	-0.09	310	150
N38	-0.09	310	80
N38H	-0.09	310	120
N38SH	-0.09	310	150
N40	-0.09	310	80
N40H	-0.09	310	120
N40SH	-0.09	310	150
N42	-0.09	310	80
N45	-0.09	310	80

# 8c - Properties (Physical)

	Density (g/cm³)	Tensile Strength (PSI)	Modulus of elasticity (PSI)	Hardness (Rockwell)	Coefficient of thermal expansion (10 <sup>-6</sup> per °C) Perpendicular to orientation	Coefficient of thermal expansion (10 <sup>-6</sup> per °C) Parallel to orientation	Electrical Resistivity at 20°C (Ohm-cm x 10 <sup>-6</sup> )
N30	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N30H	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N30SH	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N35	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N35H	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N35SH	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N38	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N38H	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N38SH	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N40	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N40H	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N40SH	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N42	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160
N45	7.4	12000	22 x 10 <sup>6</sup>	55	4.8	3.4	160



Atlas Way, Sheffield, UK, S4 7QQ

Tel: +44 (0)114 225 0600 Fax: +44 (0)114 225 0600

## 9- Stability and Reactivity

Stable at normal temperatures Avoid moist atmospheres

### 10-Disposal Considerations

Do not dispose into watercourses Use only licensed contractors Dispose in accordance with Special Waste Regulations 1996

## 11-Transport Information

Not Classified as Hazardous for Transportation by Air or Sea. Magnetic fields within 0.00525gauss at 15 feet, as legislation states.

This Data sheet is needed to accompany our commercial invoice with freight.

## 12- Regulatory Information

1– Risk & Safety - Avoid Entrapment of Body Parts

Dispose of material in a safe way

2– Other Regulations - Health & Safety at Work Act 1974

Environmental protection Act 1990 Special Waste

Regulations 1996