

號碼(No.): CE/2019/63347 日期(Date): 2019/06/27 頁數(Page): 1 of 9

## **Test Report**

凱士士企業股份有限公司 KAI SUH SUH ENTERPRISE CO., LTD. 台北市大同區延平北路一段38號 38, YEN PING N. RD., SEC. 1, TAIPEI, TAIWAN

以下測試樣品係由申請廠商所提供及確認 (The following sample(s) was/were submitted and identified by/on behalf of the applicant as):

樣品名稱(Sample Description) UV RESISTANT NYLON CABLE TIE (抗UV紮線帶)

請參考第5頁 (PLEASE REFER TO PAGE 5) 同材質產品型號(Item No. from

the same material)

樣品材質(Sample Material) UV RESISTANT NYLON, 94V-2(BLACK)

收件日期(Sample Receiving Date) 2019/06/20

測試期間(Testing Period) 2019/06/20 to 2019/06/27

#### 測試需求(Test Requested):

(1) 依據客戶指定,參考RoHS 2011/65/EU Annex II及其修訂指令(EU) 2015/863測試編、鉛、汞、六價鉻、多溴聯 苯、多溴聯苯醚, DBP, BBP, DEHP, DIBP. (As specified by client, with reference to RoHS 2011/65/EU Annex II and amending Directive (EU) 2015/863 to determine Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, BBP, DEHP, DIBP contents in the submitted sample(s).)

(2) 其他測試項目請見下一頁. (Please refer to next pages for the other item(s).)

測試結果(Test Results) : 請參閱下一頁 (Please refer to following pages).

Troy Chang / Manager - Tec Signed for and behalf of SGS TAIWAN LTD. Chemical Laboratory - Taipei



**Test Report** 

號碼(No.): CE/2019/63347 頁數(Page): 2 of 9 日期(Date): 2019/06/27

凱士士企業股份有限公司 KAI SUH SUH ENTERPRISE CO., LTD. 台北市大同區延平北路一段38號 38, YEN PING N. RD., SEC. 1, TAIPEI, TAIWAN

#### 測試結果(Test Results)

測試部位(PART NAME)No.1 黑色塑膠 (BLACK PLASTIC)

測試項目 (Test Items)	單位 (Unit)	測試方法 (Method)	MDL	結果 (Result) No.1
鎬 / Cadmium (Cd)	mg/kg	參考IEC 62321-5 (2013),以感應耦合電 漿原子發射光譜儀檢測. / With reference to IEC 62321-5 (2013) and performed by ICP-AES.	2	n. d.
鉛 / Lead (Pb)	mg/kg	參考IEC 62321-5 (2013),以感應耦合電 漿原子發射光譜儀檢測. / With reference to IEC 62321-5 (2013) and performed by ICP-AES.	2	n. d.
汞 / Mercury (Hg)	mg/kg	參考IEC 62321-4:2013+ AMD1:2017,以 感應耦合電漿原子發射光譜儀檢測. / With reference to IEC 62321-4:2013+ AMD1:2017 and performed by ICP-AES.	2	n. d.
六價鉻 / Hexavalent Chromium Cr(VI)	mg/kg	参考IEC 62321-7-2 (2017),以UV-VIS檢 測. / With reference to IEC 62321-7- 2 (2017) and performed by UV-VIS.	8	n. d.
多溴聯苯總和 / Sum of PBBs	mg/kg	参考IEC 62321-6 (2015),以氣相層析儀 /質譜儀檢測. / With reference to IEC -62321-6 (2015) and performed by -GC/MS.	-	n. d.
一溴聯苯 / Monobromobiphenyl	mg/kg		5	n. d.
二溴聯苯 / Dibromobiphenyl	mg/kg		5	n. d.
三溴聯苯 / Tribromobiphenyl	mg/kg		5	n. d.
四溴聯苯 / Tetrabromobiphenyl	mg/kg		5	n. d.
五溴聯苯 / Pentabromobiphenyl	mg/kg		5	n. d.
六溴聯苯 / Hexabromobiphenyl	mg/kg		5	n. d.
七溴聯苯 / Heptabromobiphenyl	mg/kg		5	n. d.
八溴聯苯 / Octabromobiphenyl	mg/kg		5	n. d.
九溴聯苯 / Nonabromobiphenyl	mg/kg		5	n. d.
十溴聯苯 / Decabromobiphenyl	mg/kg		5	n. d.



號碼(No.): CE/2019/63347 日期(Date): 2019/06/27 頁數(Page): 3 of 9

# **Test Report**

凱士士企業股份有限公司 KAI SUH SUH ENTERPRISE CO., LTD. 台北市大同區延平北路一段38號 38, YEN PING N. RD., SEC. 1, TAIPEI, TAIWAN

測試項目 (Test Items)	單位 (Unit)	測試方法 (Method)	MDL	結果 (Result) No.1
多溴聯苯醚總和 / Sum of PBDEs	mg/kg	参考IEC 62321-6 (2015),以氣相層析儀 /質譜儀檢測. / With reference to IEC 62321-6 (2015) and performed by GC/MS.	_	n. d.
一溴聯苯醚 / Monobromodiphenyl ether	mg/kg		5	n. d.
二溴聯苯醚 / Dibromodiphenyl ether	mg/kg		5	n. d.
三溴聯苯醚 / Tribromodiphenyl ether	mg/kg		5	n. d.
四溴聯苯醚 / Tetrabromodiphenyl ether	mg/kg		5	n. d.
五溴聯苯醚 / Pentabromodiphenyl ether	mg/kg		5	n. d.
六溴聯苯醚 / Hexabromodiphenyl ether	mg/kg		5	n. d.
七溴聯苯醚 / Heptabromodiphenyl ether	mg/kg		5	n. d.
八溴聯苯醚 / Octabromodiphenyl ether	mg/kg		5	n. d.
九溴聯苯醚 / Nonabromodiphenyl ether	mg/kg		5	n. d.
十溴聯苯醚 / Decabromodiphenyl ether	mg/kg		5	n. d.
鄰苯二甲酸二 (2-乙基己基)酯 / DEHP	mg/kg	参考IEC 62321-8 (2017),以氣相層析儀 /質譜儀檢測. / With reference to IEC 62321-8 (2017). Analysis was performed by GC/MS.	50	n. d.
(Di- (2-ethylhexyl) phthalate) (CAS No.: 117-81-7)				
鄰苯二甲酸丁苯甲酯 / BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7)	mg/kg		50	n.d.
鄰苯二甲酸二丁酯 / DBP (Dibutyl phthalate) (CAS No.: 84-74-2)	mg/kg		50	n. d.
鄰苯二甲酸二異丁酯 / DIBP (Di-isobutyl phthalate) (CAS No.: 84-69-5)	mg/kg		50	n. d.
鄰苯二甲酸二異癸酯 / DIDP (Di- isodecyl phthalate) (CAS No.: 26761- 40-0; 68515-49-1)	mg/kg		50	n. d.
鄰苯二甲酸二異壬酯 / DINP (Di- isononyl phthalate) (CAS No.: 28553- 12-0; 68515-48-0)	mg/kg		50	n. d.
鄰苯二甲酸二正辛酯 / DNOP (Di-n-octyl phthalate) (CAS No.: 117-84-0)	mg/kg		50	n. d.
鄰苯二甲酸二正己酯 / DNHP (Di-n-hexyl phthalate) (CAS No.: 84-75-3)	mg/kg		50	n. d.



號碼(No.): CE/2019/63347 日期(Date): 2019/06/27 頁數(Page): 4 of 9

# **Test Report**

凱士士企業股份有限公司 KAI SUH SUH ENTERPRISE CO., LTD. 台北市大同區延平北路一段38號 38, YEN PING N. RD., SEC. 1, TAIPEI, TAIWAN

#### 備註(Note):

- 1. mg/kg = ppm; 0. 1wt% = 1000ppm
- 2. MDL = Method Detection Limit (方法偵測極限值)
- 3. n.d. = Not Detected (未檢出)
- 4. "-" = Not Regulated (無規格值)



號碼(No.): CE/2019/63347 日期(Date): 2019/06/27 頁數(Page): 5 of 9 **Test Report** 

凱士士企業股份有限公司 KAI SUH SUH ENTERPRISE CO., LTD. 台北市大同區延平北路一段38號 38, YEN PING N. RD., SEC. 1, TAIPEI, TAIWAN

同材質產品型號 (Item No. from the same material):

AWS, PC, AP, ATC, MMR, TV, BCS, UC, KUC, TS, PTS, DCC, RC, CTF, SN, DN, CAP, CATV, KFC, KFS, MAT, BE, BT, CTT, CE, CDW, DR, DCV, RDCV, KTV, DL, DK, DR, BGQ, PAQ, HL, ES, CV, FC, FCT, FCP, FCW, BG, SR, SR, FD, HBW, HTN, HTP, HTS, HP, HPA, RHR, FCV, RRCV, TV, STV, LD3, LE, LK, LX, LQT, LQ, LDT, LY, LG3, LG, LH, LHN, PLU, LHK, PLK, PLM, PLX, PLW, PLD1, PLD2, PLD4, PLT, PLR, PCL, KWS, WS, MT, MS, MCV, KW, TCV, TCVS, TTB, MFC, KG-N, PCC, TRH, PG, AG, AGJ, EG, NPT, PG, AG, EG, AGJ, EGH, AGH, NPTH, AGJH, CV, NV, CVT, LT, CVS, ES, PH, CS, MCS, LCA, SP, SPA, SPB, SPC, SPD, DS, EB, MS, BMS, HMS, TMS, MMS, MMR, KCS, SPS, PB, PST, HGS, GS, SWS, LCS, LCL, PCU, PF, PN, PL, PHV, PCV, PCVS, PFVS, PGV, PSV, PWVS, PWV, PRVS, PDV, PUV, RPFVS, PS, PHC, PFS, M, M, AG, EG, AGJ, NPT, HV, HVC, RCV, HRCV, RS, NPTA, SR, RSP, RW, PMA, HC, CS, CSA, RLS, SCS, SR, MSP, PSP, SCT, 4J, 6J, 8J, 10J, 11J, 12J, HC, VC, FC, SWC, SNB, SB, RSB, OSB, SR, SN, SR, KS, SPR, SGN, ST, SR, TH, TH, THR, TR, TW, TRW, TT, TTU, CH, WR, FC, WH, WCT, JWS, JWB, DWS, OWS, PWS, BWS, TWS, RH, RWS, LWS, RCS, SM, EGL, AGL, NPTL, AGJL, EGH, AGH, NPTH, AGJH, SM, PG%M, LCH, SHW, RC, BPA, VF, DT, CHV, VA, BA, BV, STT, A, DP, AH, T, DV, DE, DP, HB, SWD, CAG, CEG, RSC SERIES



**Test Report** 

號碼(No.): CE/2019/63347 日期(Date): 2019/06/27 頁數(Page): 6 of 9


凱士士企業股份有限公司 KAI SUH SUH ENTERPRISE CO., LTD. 台北市大同區延平北路一段38號 38, YEN PING N. RD., SEC. 1, TAIPEI, TAIWAN

#### 重金屬流程圖 / Analytical flow chart of Heavy Metal

根據以下的流程圖之條件,樣品已完全溶解。(六價鉻測試方法除外)

These samples were dissolved totally by pre-conditioning method according to below flow chart. (Cr6+ test method excluded)

- 測試人員:陳恩臻 / Technician: Rita Chen
- 測試負責人:張啟興/Supervisor: Troy Chang





# **Test Report**

號碼(No.): CE/2019/63347 日期(Date): 2019/06/27 頁數(Page): 7 of 9


凱士士企業股份有限公司 KAI SUH SUH ENTERPRISE CO., LTD. 台北市大同區延平北路一段38號 38, YEN PING N. RD., SEC. 1, TAIPEI, TAIWAN

#### 多溴聯苯/多溴聯苯醚分析流程圖 / Analytical flow chart - PBB/PBDE

測試人員:涂雅苓 / Technician: Yaling Tu

測試負責人:張啟興 / Supervisor: Troy Chang

初次測試程序 / First testing process -選擇性篩檢程序 / Optional screen process • • • 確認程序 / Confirmation process \_ · \_ •





# **Test Report**

凱士士企業股份有限公司 KAI SUH SUH ENTERPRISE CO., LTD. 台北市大同區延平北路一段38號

38, YEN PING N. RD., SEC. 1, TAIPEI, TAIWAN

#### 可塑劑分析流程圖 / Analytical flow chart - Phthalate

日期(Date): 2019/06/27


頁數(Page): 8 of 9

測試人員:涂雅苓 / Technician: Yaling Tu

號碼(No.): CE/2019/63347

測試負責人:張啟興 / Supervisor: Troy Chang

【測試方法/Test method: IEC 62321-8】





# **Test Report**

凱士士企業股份有限公司 KAI SUH SUH ENTERPRISE CO., LTD. 台北市大同區延平北路一段38號

38, YEN PING N. RD., SEC. 1, TAIPEI, TAIWAN

號碼(No.): CE/2019/63347

\* 照片中如有箭頭標示,則表示為實際檢測之樣品/部位. \* (The tested sample / part is marked by an arrow if it's shown on the photo.)

日期(Date): 2019/06/27

頁數(Page): 9 of 9

CE/2019/63347



\*\* 報告結尾 (End of Report) \*\*